

Ultra-high-quality factor and ultra-high accelerating gradient achievements in a 1.3 GHz continuous wave cryomodule

Authors: Jin-Fang Chen, Yue Zong, Xiao-Yun Pu, Sheng-Wang Xiang, Shuai Xing, Zheng Li, Xu-Ming Liu, Yan-Fei Zhai, Xiao-Wei Wu, Yong-Zhou He, Ling-Ling Gong, Ji-Dong Zhang, Shan-Shan Cao, Wen-Ding Fan, Bin-Tuan Zhang, Kai Xu, Yi-Bo Yu, Guang-Hua Chen, Li-Jun Lu, Ya-Wei Huang, Shen-Jie Zhao, Hong-Tao Hou, Zhen-Yu Ma, Ye-Liang Zhao, Xiang Zheng, Jiu-Ce Sun, Sen Sun, Zhi-Qiang Jiang, Yu-Bin Zhao, Meng Zhang, Ying-Bing Yan, Yi-Yong Liu, Qiang Gu, Bo Liu, Li-Xin Yin, Dong Wang, Hai-Xiao Deng, Zhen-Tang Zhao, Hai-Xiao Deng

Date: 2024-12-15T00:00:00+00:00

Abstract

We report the world-leading performance of a 1.3 GHz cryomodule equipped with eight 9-cell superconducting radio-frequency cavities that underwent a medium-temperature furnace baking process. During continuous wave horizontal testing, these cavities achieved unprecedented average intrinsic quality factors of 4.0×10^{10} at 20 MV/m and 3.2×10^{10} at 29 MV/m, with no instances of field emission. The cryomodule demonstrates near-complete preservation of ultra-high-quality factors and ultra-high accelerating gradients from vertical to horizontal testing, marking a significant milestone in continuous-wave superconducting radio-frequency accelerator technology. This letter presents the cryomodule development experience, including cavity preparation, cryomodule assembly, degaussing, fast cooldown, and performance testing.

Full Text

Preamble

Ultra-high-quality factor and ultra-high accelerating gradient achievements in a 1.3 GHz continuous wave cryomodule*

Jin-Fang Chen,¹ Yue Zong,¹ Xiao-Yun Pu,¹ Sheng-Wang Xiang,¹ Shuai Xing,¹ Zheng Li,¹ Xu-Ming Liu,¹ Yan-Fei Zhai,¹ Xiao-Wei Wu,² Yong-Zhou He,¹ Ling-Ling Gong,¹ Ji-Dong Zhang,¹ Shan-Shan Cao,¹ Wen-Ding Fang,¹ Bin-Tuan

Zhang,¹ Kai Xu,¹ Yi-Bo Yu,¹ Guang-Hua Chen,¹ Li-Jun Lu,¹ Ya-Wei Huang,³ Shen-Jie Zhao,¹ Hong-Tao Hou,¹ Zhen-Yu Ma,¹ Ye-Liang Zhao,¹ Xiang Zheng,¹ Jiu-Ce Sun,³ Sen Sun,¹ Zhi-Qiang Jiang,¹ Yu-Bin Zhao,¹ Meng Zhang,¹ Ying-Bing Yan,¹ Yi-Yong Liu,¹ Qiang Gu,¹ Bo Liu,¹ Li-Xin Yin,¹ Dong Wang,¹ Hai-Xiao Deng,^{1,†} and Zhen-Tang Zhao¹

¹Shanghai Advanced Research Institute, Chinese Academy of Sciences, Shanghai 201204, China

²Zhangjiang Laboratory, Shanghai 201210, China

³ShanghaiTech University, Shanghai 201210, China

We report the world-leading performance of a 1.3 GHz cryomodule equipped with eight 9-cell superconducting radio-frequency cavities that underwent a medium-temperature furnace baking process. During continuous wave horizontal testing, these cavities achieved unprecedented average intrinsic quality factors of 4.0×10^{10} at 20 MV/m and 3.2×10^{10} at 29 MV/m, with no instances of field emission. The cryomodule demonstrates near-complete preservation of ultra-high-quality factors and ultra-high accelerating gradients from vertical to horizontal testing, marking a significant milestone in continuous-wave superconducting radio-frequency accelerator technology. This letter presents the cryomodule development experience, including cavity preparation, cryomodule assembly, degaussing, fast cooldown, and performance testing.

Keywords: SRF cryomodule • Mid-T baking • High quality factor • High accelerating gradient

INTRODUCTION

High Q_0 (quality factor) cryomodules equipped with superconducting radio-frequency (SRF) cavities are key components of modern accelerators, such as high-repetition X-ray FEL facilities [?], high-power extreme ultraviolet lithography light sources [?], and other future high-duty factor colliders [?]. At the Shanghai High Repetition Rate XFEL and Extreme Light Facility (SHINE) [?], more than 50 high Q_0 cryomodules operating in 1.3 GHz continuous wave (CW) mode will be installed to generate an 8 GeV electron beam. In contrast, extreme ultraviolet lithography light sources require approximately 10 high- Q_0 cryomodules operating in 1.3 GHz CW mode for a 1 GeV energy recovery linac. Generally, a high Q_0 cryomodule includes eight 9-cell TESLA cavities [?], eight fundamental power couplers (FPC), one superconducting quadrupole magnet package, and one cold beam-position monitor. The design and advancements of 1.3 GHz cryomodules are primarily attributed to the R&D efforts undertaken in large-scale facilities like the TESLA Test Facility [?], the European XFEL [?], the Linac Coherent Light Source II (LCLS-II) [?], LCLS-II HE [?] and SHINE.

Currently, nitrogen doping (N-doping) [?–?] and medium-temperature (mid-T) baking [?–?] are the two main methods used to enhance the Q_0 values of SRF cavities made of high-purity niobium. N-doping incorporates nitrogen atoms as interstitial impurities into the niobium lattice, lowering the

mean free path of the RF penetration layer of niobium, hence the BCS resistance, and reducing the residual resistance [?]. Fermilab and Jefferson Lab developed cryomodules equipped with SRF cavities treated by 2/6 N-doping recipes for LCLS-II [?, ?]. In 2023, 35 cryomodules with 2/6 N-doped cavities were commissioned for the LCLS-II, demonstrating Q_0 of 2.8×10^{10} at an average accelerating gradient of 16 MV/m in the CW operation of a superconducting linac [?]. The LCLS-II-HE cryomodule with a 2/0 N-doping recipe achieved a maximum acceleration voltage of 208 MV in CW mode, corresponding to an average accelerating gradient of 25.1 MV/m, and Q_0 of 3.0×10^{10} at a gradient of 21 MV/m [?]. Mid-T baking is a novel and simplified high- Q_0 recipe that yields results similar to those of N-doping, while preventing the formation of NbN precipitates, which act as defects, and reducing the risk of contamination. The Institute of High Energy Physics (IHEP) developed the first high- Q_0 cryomodule equipped with eight mid-T-baked cavities, achieving Q_0 of 3.8×10^{10} at 16 MV/m and Q_0 of 3.6×10^{10} at 21 MV/m in horizontal testing [?].

At the Shanghai Advanced Research Institute (SARI), we conduct experimental cavity treatments using facilities for SRF cavity surface treatments on a platform located in Wuxi, China [?]. Both N-doped and mid-T baking recipes have been studied, achieving high accelerating gradients exceeding 25 MV/m on 1.3 GHz 9-cell cavities [?]. Since 2020, several sets of cryomodules with high- Q_0 cavities have been assembled and tested [?]. In this letter, we report the first 1.3 GHz high Q_0 cryomodule dedicated to CW operation up to 1 mA, developed at SARI. It is equipped with eight mid-T-baked cavities and eight 30 kW FPCs [?, ?], demonstrating world-leading, ultrahigh Q_0 and ultrahigh accelerating gradient performance in CW horizontal testing.

II. MID-T BAKED CAVITIES

The eight cavities were mechanically fabricated by the HE-Racing Technology Company in Beijing, treated by the SHINE cavity surface treatment facilities in Wuxi [?], and tested at the SARI and IHEP vertical test (VT) stands. These cavities underwent 200 μm electropolishing, 3 h of 900°C high-temperature baking, exposure to air, and 3 h of furnace baking at 300°C [?].

Fig. 1 [Figure 1: see original paper] shows the vertical test results of the eight dressed cavities. The solid triangle represents the Q_0 value, while the hollow triangle represents the radiation dose. The Q_0 values are corrected by 0.8 n Ω loss of stainless-steel flanges. The three cavities with significant radiation dose were cleaned again by high-pressure rinsing before delivery to the cryomodule assembly, without additional vertical testing. The sudden drop of Q_0 at around 16 MV/m for FV007-J, 23 MV/m for FV006-J, and 25 MV/m for GY002-J is attributed to flux trapping after soft quenches caused by multipacting [?], which can be recovered after warming up and performing a fast cooldown. For a direct comparison between the vertical and horizontal tests, the Q_0 drop was compensated for by the gap. The average Q_0 was 4.0×10^{10} at 20 MV/m, and the average maximum gradient was 29.4 MV/m. Three cavities exhibiting

field emission during the vertical test were cleaned by long, high-pressure rinsing with two rounds of six turns before delivery to the cryomodule assembly. Although no further vertical tests were performed on these three cavities due to the tight schedule, as shown in the horizontal test results, all field emissions were eliminated.

III. CRYOMODULE ASSEMBLY

The cryomodule assembly includes clean assembly of the cavity string in a class 10 cleanroom, the cold mass, and the final assembly, typically completed within approximately two months. Before string assembly, all cavities underwent an outer surface rinsing process, after which they entered the cleanroom for more thorough cleaning, including wiping the outer surface, particularly the helium vessel bellows. The surface was blown with clean nitrogen gas to verify contamination levels met class 10 cleanroom standards. The assembly process began with the installation of fundamental power couplers, followed by intercavity bellows from upstream to downstream. Fig. 2 [Figure 2: see original paper] shows the cavity-string assembly of the SARI cryomodule (CM) in a class 10 cleanroom.

During assembly, nitrogen gas was vented into the cavities at 1 slm to maintain slightly positive pressure, preventing contamination from entering. Once the string assembly was completed, positive-pressure leak detection was conducted to identify major leaks. The cavity string was then evacuated into a vacuum, followed by a second leak test under vacuum conditions. Residual gas analysis assessed the cleanliness of the entire cavity string. After completing these tests, the cavity string was backfilled with nitrogen to a pressure of 1050 mbar, slightly higher than atmospheric pressure, for protection, and subsequently transported out of the cleanroom for further assembly.

IV. DEGAUSSING AND COOLING DOWN

The cryostat was first degaussed in an east-west direction at SARI. During cryomodule assembly, two flux gates were mounted along the beam direction at the cavity 1# and 5# slots between the two layers of magnetic shields outside the cavity helium vessel. After the cryomodule was installed on the horizontal test stand, the entire cryomodule was degassed at room temperature, as shown in Fig. 3(a) [Figure 3: see original paper]. The magnetic field falls from 2.6 mGs to 0.3 mGs and from 0.9 mGs to 0.7 mGs after degaussing for the cavities 1# and 5#, respectively, as shown in Fig. 3(b) [Figure 3: see original paper].

The SARI cryomodule cooling process, from 300 K to 2 K, follows a procedure similar to that of the European XFEL [?] and LCLS-II [?], typically lasting for 3–4 days. From 300 K to 45 K, the average cooling rate has been controlled at around 6 K/h, followed by a “stand-by mode” lasting for about 12 hours to allow the entire cryomodule cold mass to stabilize at the 45 K temperature level. Fast cooling from 45 K to 4.5 K is required for magnetic flux exclusion in high- Q

cavities, improving RF performance [?]. Once liquid helium accumulates along the cavity string and in the two-phase pipe, most of the cold mass is cooled to approximately 4.5 K. Final cooling is achieved by depressurizing the saturated helium vapor from around 1.2 bar to 31 mbar, reaching the operating condition at 2 K superfluid helium. Fig. 4 [Figure 4: see original paper] shows the first cooling step of the standard SARI cryomodule.

A key method to achieve high Q_0 performance at 2 K is to maintain an instant liquid-helium mass flow rate, creating a sufficient thermal gradient for magnetic flux expulsion as the cavities pass through the superconducting transition point (T_c) of approximately 9.2 K [?, ?]. Before the Q_0 test, the cryomodule was warmed up to 45 K and then quickly cooled again to release the magnetic flux trapped during previous quenches, which reached their maximum gradient or were induced by multipacting. For the SARI cryomodule, a maximum flow rate of 41.6 g/s was achieved when the cavities passed through the T_c . Fig. 5 [Figure 5: see original paper] shows the thermal difference between the top and bottom of the dressed cavities during the horizontal test, where thermal sensors are mounted outside dressed cavities 1#, 5# and 8#.

V. Q_0 PERFORMANCE

The mass flow rate method was employed to measure the static and dynamic 2 K heat load of the cryomodule [33–35]. Fig. 6 [Figure 6: see original paper] shows the calibration results of the heat load via heaters for the SARI CM. The CM was first injected with liquid helium above half of the two-phase pipe and then evaporated in a semi-closed system (i.e., a cavity string with supply valves closed and the helium-gas-return pipe valve opened) under different heat load conditions ranging from 0 to 90 W. According to the law of conservation of energy, when dynamic balance is achieved, the helium evaporating mass flow rate, along with its latent heat (23 J/g at 2 K) takes the same energy deposited on the 2 K cold mass from the outside heat load. With the above relationship between heat load and evaporating mass flow rate, a linear fit can be obtained based on the thermal heater power and flowmeter measurements. Consequently, the absolute value of the intercept point at “zero” mass flow rate gives the 2 K static heat load of the SARI cryomodule around 21.7 W, as shown in Fig. 6.

Fig. 6 shows the static heat load measurements for the SARI cryomodule at 2 K: the overlap of circles at 20, 30, and 80 W serves to verify the data’s repeatability and reliability. The dynamic heat load of each cavity was measured by subtracting the heat load of three cavities from four cavities to improve accuracy. The estimated measurement uncertainty of Q_0 was less than 10%, and the accelerating gradient was less than 5%.

To directly compare Q_0 between vertical and horizontal tests, Q_0 values with a sudden drop in three cavities were compensated for by the gap at the drop gradient. Fig. 7 [Figure 7: see original paper] shows a comparison of Q_0 at 20 MV/m for the eight dressed cavities in both vertical and horizontal tests.

The average Q_0 values at 166 MV and higher voltages in CW mode were also measured for the SARI CM. The total 2 K heat load was 104.9 W at a total voltage of 166.1 MV with all eight cavities at 20 MV/m, 194.9 W at 223.8 MV, and 236.4 W at 241.3 MV, corresponding to an average Q_0 of 4.0×10^{10} at a gradient of 20 MV/m, 3.4×10^{10} at 27 MV/m, and 3.2×10^{10} at 29 MV/m, respectively. Fig. 8 [Figure 8: see original paper] provides the measurement points of the SARI CM and compares them with other top cryomodules [?, ?].

VI. GRADIENT PERFORMANCE

Fig. 9 [Figure 9: see original paper] shows the maximum accelerating gradients for the eight dressed cavities measured in CW mode during vertical tests and in the cryomodule, where the maximum gradient is defined as stable operation for at least one minute. The usable gradient in the cryomodule is defined as meeting the conditions of being 0.5 MV/m less than the quench field, stable operation for one hour, and radiation dose less than 500 $\mu\text{Sv/h}$ measured by the G-M tube radiation detectors placed around 2 m from the cryomodule in the horizontal test stand. As can be seen, all cavities approach full-gradient performance except for cavity 5#, which is limited by HOM heating, as described below.

To accelerate a beam, long-term stable operation at the working gradient is essential for the CM. During operation, RF power can heat the FPC antennas, which are cooled through a ceramic window and CF100 flange by a 45 K intercept, a conduction-cooling braid connected to the 45 K helium gas pipes, eventually reaching thermal equilibrium. For the SARI CM, the temperature of each CF100 flange was monitored using thermal sensors. A stable operation test was performed at 220 MV for the SARI CM. The external Q values of the eight cavities were adjusted to their optimal values of approximately 6.1×10^7 for a working gradient of 20 MV/m. Due to the cryogenic limit of the horizontal test stand, the eight cavities were split into two groups for stable operation testing. Each cavity operated at 27.3 MV/m, except for cavity 5# at 21.7 MV/m. The group with the first four cavities maintained a total voltage of 113 MV, while the other group maintained 108 MV. To reduce test time, we detuned the phase of the self-excited loop to increase reflected power, thus heating the main coupler to its threshold of approximately 150 K. Afterward, we tuned it back and awaited thermal equilibrium, or maintained it for 10 hours. Fig. 10 [Figure 10: see original paper] shows the temperature behavior of the eight FPC CF100 flanges during the 220 MV stable operation test. As shown, all the temperatures of the eight CF100 flanges decreased, reaching quasi-equilibrium, with a maximum temperature of less than 120 K, below the 150 K threshold. This confirms the stable operation capacity at 220 MV for this CM.

VII. LIMITATION FACTOR

When comparing the RF performances of the eight cavities in the vertical and horizontal tests, cavity 5# exhibited a significant decrease in the accelerating

gradient. The maximum CW operating gradient for cavity 5# was limited to approximately 25.2 MV/m by quenching, accompanied by a rapid temperature increase at the FPC-side HOM coupler, where the thermal sensor was mounted on the copper clamp at the copper sleeve of the HOM feedthrough, as shown in Fig. 11 [Figure 11: see original paper].

To investigate the limiting factor, we tested cavity 5# in pulsed mode. With a repetition rate of 0.5 Hz and a duty cycle of 5%, we began increasing the input power to the cavity, which showed that the cavity could stably operate at 29.2 MV/m, similar to the maximum gradient in the vertical test, with a slight temperature increase at the FPC-side HOM. We then gradually increased the duty cycle in steps of 5%, while maintaining a gradient of 29.2 MV/m, and a positive correlation between the FPC-side HOM temperature and duty cycle was observed. The cavity could stably operate at 29.2 MV/m with a duty cycle of up to 40%, where the HOM temperature approached approximately 40°C, but quenched quickly once the duty cycle was increased to 45%. Fig. 12 [Figure 12: see original paper] shows the relationship between the HOM temperature and the duty cycle for cavity 5#. It is important to note that no field emissions were observed during these measurements. Therefore, we concluded that the limitation of cavity 5# gradient is due to overheating of the HOM antenna.

Table 1 summarizes the CW mode performances of the eight mid-T-baked cavities in VT and CM. The Q_0 of the entire CM measurement was 4.0×10^{10} at 166 MV, with all eight cavities operating simultaneously at 20 MV/m. The slight difference in the average Q_0 between the individual cavities and the entire CM measurement was likely due to the uncertainty of the small heat load, as shown in Fig. 6.

It is worth mentioning that the cryomodule was also tested in pulsed mode with a repetition rate of 0.5 Hz and a 10% duty factor, where the total accelerating voltage reached 247.6 MV. In this mode, cavity 5# was powered up to 29.2 MV/m, the same as its maximum gradient in the vertical test. Additionally, no detectable field emissions were observed during any of the cryomodule tests.

VIII. CONCLUSIONS

A high Q_0 cryomodule equipped with eight mid-T-baked 1.3 GHz 9-cell cavities was assembled and tested at SARI. This cryomodule achieved an ultra-high average Q_0 at the operating gradients and an unprecedented total accelerating voltage in CW mode. The cryomodule's average Q_0 was 4.0×10^{10} at 20 MV/m and 3.2×10^{10} at 29 MV/m in the horizontal test, which corresponds to a maximum CW RF voltage of approximately 241 MV. The RF performance of the cavities was well-maintained from the vertical test to the horizontal test. Furthermore, no field emissions were observed in any of the eight cavities in the cryomodule. The successful development of this ultra-high Q_0 and ultra-high gradient cryomodule demonstrates the techniques mastered from components to a completed cryomodule, marking an important milestone for CW accelera-

tor projects, such as high-repetition X-ray FEL facilities, high-power extreme ultraviolet lithography light sources, and other future high-duty factor colliders.

Acknowledgments

The authors would like to thank all the colleagues who contributed to this work, including the SRF cryomodule, cryogenic, and general technology teams, as well as the companies and institutes that supplied the cryomodule components and technical servers. The authors are grateful to Mi-Yi-Min Zhao and Xing-Heng Wang for the helps in figure drawing.

References

- [1] N. Huang, H. Deng, B. Liu et al., Features and futures of X-ray free-electron lasers. *The Innovation* 2, 100097 (2021). <https://doi.org/10.1016/j.xinn.2021.100097>
- [2] N. Nakamura, R. Kato, H. Sakai et al., High-power EUV free-electron laser for future lithography. *Jpn. J. Appl. Phys.* 62, SG0809 (2023). <https://doi.org/10.35848/1347-4065/acc18c>
- [3] J. Gao, CEPC Technical Design Report: Accelerator. *Radiat Detect Technol Methods* 8, 1–1105 (2024). <https://doi.org/10.1007/s41605-024-00463-y>
- [4] N. Huang, Z. Liu, B. Deng et al., The MING proposal at SHINE: megahertz cavity enhanced X-ray generation. *Nucl. Sci. Tech.* 34, 6 (2023). <https://doi.org/10.1007/s41365-022->
- [5] B. Aune, R. Bandelmann, D. Bloess et al., Superconducting TESLA cavities. *Phys. Rev. ST Accel. Beams* 3, 092001 (2000). <https://doi.org/10.1103/PhysRevSTAB.3.092001>
- [6] C. Pagani, J. Weisend II, R. Bandelmann et al., Construction, Commissioning, and Cryogenic Performances of the First TESLA Test Facility (TTF) Cryomodule. *Advances in Cryogenic Engineering* 43. https://doi.org/10.1007/978-1-4757-9047-4_9
- [7] C. Madec, S. Berry, P. Charon et al., Status of E-XFEL String and Cryomodule Assembly at CEA-Saclay. in *Proceedings of LINAC2012*, Tel-Aviv, Israel, 2012.
- [8] T. Arkan, C. Ginsburg, Y. He et al., LCLS-II 1.3 GHz Design Integration for Assembly and Cryomodule Assembly Readiness at Fermilab. in *Proceedings of SRF2015*, Whistler, BC, 2015.
- [9] J. Maniscalco, LCLS-II-HE cavity and cryomodule test progress. *TESLA Technology Collaboration (TTC) Meeting*, Fermilab, Batavia, IL, 2023.
- [10] A. Grassellino, A. Romanenko, D. Sergatskov et al., Nitrogen and argon doping of niobium for superconducting radio frequency cavities: a pathway to highly efficient accelerating structures. *Supercond. Sci. Technol.* 26, 102001 (2013). <https://doi.org/10.1088/0953-2048/26/10/102001>
- [11] A. Palczewski, Analysis Of Bcs Rf Loss Dependence On N-doping Protocols. in *Proceedings of SRF2015*, Whistler, BC,
- [12] D. Bafia, Optimization of High Temperature Nitrogen Doping TESLA Technology Collaboration (TTC) Meeting, 2018
- [13] Y. Zong, J. Chen, D. Wang et al., Accelerating gradient superconducting Instrum. 168724 (2023). *radio-frequency Methods Phys. Res. Sec. A* 1057, <https://doi.org/10.1016/j.nima.2023.168724> cavities SHINE. *Nucl. nitrogen-*

doped improvement

- [14] P. Dhakal, Nitrogen doping and infusion in SRF cav-100034 (2020). A review. *Physics Open* 5, ities: <https://doi.org/10.1016/j.physo.2020.100034>
- [15] S. Posen, A. Romanenko, A. Grassellino et al., Ultra-Low Surface Resistance via Vacuum Heat Treatment of Superconducting Radiofrequency Cavities. *Phys. Rev. Applied* 13, 014024 (2019). <https://doi.org/10.1103/PhysRevApplied.13.014024>
- [16] H. Ito, H. Araki, K. Takahashi et al., Influence of Furnace Baking on Q-E Behavior of Superconducting Accelerating Cavities. *Prog Theor Exp Phys* 2021, 071G01 (2021). <https://doi.org/10.1093/ptep/ptab056>
- [17] F. He, W. Pan, P. Sha et al., Medium-temperature furnace baking of 1.3 GHz 9-cell superconducting cavities at IHEP. *Superconductor Science and Technology* 34, 095005 (2021). <https://doi.org/10.1088/1361-6668/ac1657>
- [18] H. Padamsee, nology for Accelerators - state of (WILEY-VCH GmbH, <https://doi.org/10.1002/9783527836314> trends Superconducting Radiofrequency Tech- the art and emerg- 2023.),
- [19] G. Wu, A. Grassellino, E. Harms et al., Achievement of Ultra-High Quality Factor in Prototype Cryomodule (2018). <https://doi.org/10.48550/arXiv.1812.09368> arXiv:181209368, LCLS-II.
- [20] R. Legg, G. Cheng, E. Daly et al., LCLS-II Cryomodule Production at JLab. in *Proceedings of SRF2017*, Lanzhou, China,
- [21] S. Posen, A. Cravatta, M. Checchin et al., High gradient performance and quench behavior of a verification cryomodule for a high energy continuous wave linear accelerator. *Phys. Rev. Accel. Beams* 25, 042001 (2022). <https://doi.org/10.1103/PhysRevAccelBeams.25.042001>
- [22] W. Pan, J. Zhai, F. He et al., High Q and high gradient performance of first medium-temperature baking 1.3 GHz cryomodule. *Phys. Rev. Accel. Beams* 27, 092003 (2024). doi: <https://doi.org/10.1103/PhysRevAccelBeams.27.092003>
- [23] J. Chen, S. Xing, J. Wu et al., Design, construction and operation of a surface-treatment platform for SHINE superconducting cavities. in *Proceedings of IPAC'24*, Nashville, TN, USA,
- [24] Y. Zong, Q. Chen, X. Huang et al., Realization of accelerating gradient larger than 25 MVm on high-Q 1.3 GHz 9-cell cavities for SHINE. in *Proceedings of SRF2023*, Grand Rapids, MI, USA, 2023.
- [25] J. Chen, H. Hou, Z. Ma et al., Cryomodules development for SHINE project. in *Proceedings of IPAC'24*, Nashville, TN, USA, 2024.
- [26] Z. Ma, Lessons learned on coupler fabrication for SHINE. *TTC2024 Meeting*, ESS Lund, Sweden, 2024.
- [27] Z. Ma, H. Hou, S. Zhao, et al., Manufacturing studies and rf the 1.3 GHz fundamental power coupler prototypes. *Phys. Rev. Accel. Beams* 25, 113501 (2022).<https://doi.org/10.1103/PhysRevAccelBeams.25.113501> results of
- [28] D. Bafia, A. Grassellino, A. Romanenko et al., New Insights on Nitrogen Doping. in *Proceedings of SRF2019*, Dresden, Germany, 2019.
- [29] A. Navitski, Cavities/modules test facility AMTF at DESY. *Americas Workshop on Linear Colliders 2014*, Fermilab, 2014.
- [30] G. Wu, E. Harms, A. Grassellino et al., Performance of the high Q CW prototype cryomodule for LCLS-II at FNAL. in *Proceedings of SRF2017*,

Lanzhou, China, 2017.

- [31] S. Posen, G. Wu, A. Grassellino et al., Role of magnetic flux expulsion to reach $Q_0 > 3 \times 10^{10}$ in superconducting rf cryomodules. Phys. Rev. Accel. Beams 22, 032001 (2019). <https://doi.org/10.1103/PhysRevAccelBeams.22.032001>
- [32] D. Gonnella, R. Eichhorn, F. Furuta et al, Nitrogen-doped 9-cell cryomodule for LCLS-II. J. Appl. Phys. 117, 023908 (2015). cavity performance <https://doi.org/10.1063/1.4905681>
- [33] X. Wang, S. Barbanotti, J. Eschke et al., Thermal performance analysis and measurements of the prototype cryomodules of European XFEL accelerator—Part II. Nucl. Instrum. Methods Phys. Res. Sec. A 763, 688-700 (2014). <https://doi.org/10.1016/j.nima.2014.07.045>
- [34] E. Harms, LCLS-II cryomodule heat load measurements at Fermilab. TESLA Technology Collaboration (TTC) Meeting,
- [35] W. Pan, R. Ge, M. Li et al., Cryogenic system of the high performance 1.3 GHz 9-cell superconducting radio frequency prototype cryomodule. Applied Thermal Engineering 255, 124042 (2024). <https://doi.org/10.1016/j.applthermaleng.2024.124042>

Author Contributions

All authors contributed to and participated in the design, manufacturing, assembly, and testing of the cryomodule. Jin-Fang Chen was the cryomodule coordinator. Hai-Xiao Deng was the project leader. The first draft of the manuscript was written by Jin-Fang Chen, Meng Zhang, Hai-Xiao Deng and all authors commented and reviewed on previous versions and the final version of the manuscript.

Note: Figure translations are in progress. See original paper for figures.

Source: ChinaXiv — Machine translation. Verify with original.